

LG CHEMICAL (GUANGZHOU) ENGINEERING PLASTICS CO LTD

1 YECHENG 1ST RD, EAST SEC OF ECONOMIC & TECH DEV DIST, GUANGZHOU
GUANGDONG 510760 CN

HI-121H**Acrylonitrile Butadiene Styrene (ABS), furnished as pellets**

Color	Min Thk (mm)	Flame Class	Flame		RTI		RTI Str
			HWI	HAI	Elec	Imp	
ALL	1.5	HB	3	0	60	60	60
	3.0	HB	3	1	60	60	60

Comparative Tracking Index
(CTI): **0**

Dimensional Stability (%): **0**

High-Voltage Arc Tracking Rate
(HVTR): **2**

High Volt, Low Current Arc Resis
(D495): **6**

Dielectric Strength (kV/mm): **27**

Volume Resistivity (10^x ohm-cm) : **15**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents.

ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2004-09-23

Last Revised: 2009-04-09 Underwriters Laboratories Inc®

IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
			3.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-

IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m^2	-	-
ISO Izod Impact	ISO 180	kJ/m^2	-	-
ISO Charpy Impact	ISO 179-2	kJ/m^2	-	-

Underwriters Laboratories Inc®